AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1. (Original) A method of transporting semi-processed rubber, the method comprising locating the semi-processed rubber in a ship and supplying heat to the semi-processed rubber during transit to prevent solidification of, and/or crystallisation in, the semi-processed rubber.
- 2. (Original) A method according to Claim 1, comprising supplying sufficient heat to the semi-processed rubber to maintain its temperature above 25 °C, most preferably in a range of from 28 to 35 °C, and even more preferably in a range of from 30 to 33 °C.
- 3. (Currently Amended) A method according to Claim 1-or 2, comprising circulating heat from the ship's engine and circulating to heat the semi-processed rubber.
- 4. (Original) A method according to Claim 3, comprising circulating the water which is drawn through the engine to cool it to heat the semi-processed rubber.

National Stage of PCT/GB2004/003230 Attorney Docket No. S1011/20198 Preliminary Amendment Dated January 30, 2006

- 5. (Currently Amended) A method according to any preceding Claim 1, comprising using a heat exchanger to heat circulating air, the heated air being circulated into the hold of the ship where the semi-processed rubber is stored for transport.
- 6. (Currently Amended) A method according to Claim 1—or 2, comprising heating the rubber using convection heaters, for example electrical convection heaters or blowers may be used.
- 7. (Currently Amended) A method according to any preceding—Claim_1, comprising providing insulating material between the semi-processed rubber and at least one wall of a hold in which the semi-processed rubber is stored for transport.
- 8. (Original) A method according to Claim 7, comprising inflating a collapsible bag or bladder to provide the insulating material.
- 9. (Currently Amended) A method according to any preceding Claim_1, further comprising storing the semi-processed rubber in a covered warehouse or storage facility at a departure and/or destination port, the warehouse preferably being maintained at a temperature sufficient to prevent the rubber from hardening and/or crystallising during storage.

National Stage of PCT/GB2004/003230 Attorney Docket No. S1011/20198

Preliminary Amendment Dated January 30, 2006

10. (Currently Amended) A method according to any preceding-Claim_1, further comprising

transporting the semi-processed rubber to a user in a state which is usable without

requiring further heating.

11. (Original) A method of supplying semi-processed rubber to a user in a usable form, the

method comprising tapping latex from a rubber tree, forming a cake, transporting the

cake to a local processor for semi-processing and subsequently transporting the semi-

processed rubber cake to a user and ensuring that the cake does not harden or that crystals

form in the cake during the first and/or second transportation step.

12. (Original) A method of transporting solid goods whose state is prone to alter during

transportation, the method comprising maintaining the goods at a temperature of from 25

to 35 °C during transportation by supplying heated air to the goods using heat reclaimed

from the prime mover of the means of transportation.

13. (Original) A method according to Claim 12, wherein the goods are semi-processed

rubber.

Page 5 of 7

National Stage of PCT/GB2004/003230 Attorney Docket No. S1011/20198 Preliminary Amendment Dated January 30, 2006

- 14. (Currently Amended) A method according to Claim 12-or 13, wherein at least part of said transportation takes place on a ship and said transportation means is a ship.
- 15. (Original) A method of supplying semi-processed rubber to a user, the method comprising storing the semi-processed rubber at a location which is maintained at a temperature to prevent or at least inhibit the hardening of, or formation of crystals in, the semi-processed rubber.
- 16. (Original) A method according to Claim 15, comprising maintaining the temperature of the location at or above 24°C.